# **American Nuclear Society**

### **WITHDRAWN**

January 3, 1996 ANSI/ANS-8.5-1986

use of borosilicate-glass raschig rings as a neutron absorber in solutions of fissile material

## an American National Standard

No longer being maintained as an American National Standard. This standard may contain outdated material or may have been superseded by another standard. Please contact the ANS Standards Administrator for details.



published by the American Nuclear Society 555 North Kensington Avenue La Grange Park, Illinois 60525 USA

ANSI/ANS-8.5-1986 Revision of ANSI/ANS-8.5-1979

#### American National Standard Use of Borosilicate-Glass Raschig Rings as a Neutron Absorber in Solutions of Fissile Material

Secretariat American Nuclear Society

Prepared by the American Nuclear Society Standards Committee Working Group ANS-8.5

Published by the American Nuclear Society 555 North Kensington Avenue La Grange Park, Illinois 60525 USA

Approved January 3, 1986 by the American National Standards Institute, Inc.

#### American National Standard

Designation of this document as an American National Standard attests that the principles of openness and due process have been followed in the approval procedure and that a consensus of those directly and materially affected by the standard has been achieved.

This standard was developed under the procedures of the Standards Committee of the American Nuclear Society; these procedures are accredited by the American National Standards Institute, Inc., as meeting the criteria for American National Standards. The consensus committee that approved the standard was balanced to assure that competent, concerned, and varied interests have had an opportunity to participate.

An American National Standard is intended to aid industry, consumers, governmental agencies, and general interest groups. Its use is entirely voluntary. The existence of an American National Standard, in and of itself, does not preclude anyone from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard.

By publication of this standard, the American Nuclear Society does not insure anyone utilizing the standard against liability allegedly arising from or after its use. The content of this standard reflects acceptable practice at the time of its approval and publication. Changes, if any, occurring through developments in the state of the art, may be considered at the time that the standard is subjected to periodic review. It may be reaffirmed, revised, or withdrawn at any time in accordance with established procedures. Users of this standard are cautioned to determine the validity of copies in their possession and to establish that they are of the latest issue.

The American Nuclear Society accepts no responsibility for interpretations of this standard made by any individual or by any ad hoc group of individuals. Requests for interpretation should be sent to the Standards Department at Society Head-quarters. Action will be taken to provide appropriate response in accordance with established procedures that ensure consensus on the interpretation.

Comments on this standard are encouraged and should be sent to Society Headquarters.

Published by

American Nuclear Society 555 North Kensington Avenue, La Grange Park, Illinois 60525 USA

Copyright © 1986 by American Nuclear Society.

Any part of this standard may be quoted. Credit lines should read "Extracted from American National Standard ANSI/ANS-8.5-1986 with permission of the publisher, the American Nuclear Society." Reproduction prohibited under copyright convention unless written permission is granted by the American Nuclear Society.

Printed in the United States of America

(This Foreword is not a part of American National Standard Use of Borosilicate-Glass Raschig Rings as a Foreword is not a part of American Ansi/Ans-8.5-1986.)

> This standard, which provides guidance for the use of borosilicate-glass raschig rings as a neutron absorber for criticality control in plants processing fissile materials, was first approved as N16.4-1971, revised as ANSI/ANS-8.5-1979, and this revision results from the prescribed five-year review. It recommends maximum concentrations of homogeneous solutions of uranium and plutonium in vessels of unlimited size when packed with rings. Although the general use of neutron absorbers, including raschig rings, for this purpose dates back to 1958, some applications were recorded as early as the mid-1940s.

> In this standard the concentration of solutions is expressed as the mass of plutonium or of uranium per unit volume. Limitations on the relative abundance of the various isotopes of plutonium are imposed in the specifications applicable to plutonium solutions. The limits on total uranium concentration, which are based on 100% 235U. apply to uranium of any <sup>235</sup>U content. The <sup>233</sup>U content of solutions in which <sup>235</sup>U is the principal uranium isotope is limited.

> The experimental data forming the bases for the specifications and a review of experience with raschig rings were reported by Nichols et al. at the time of initial preparation of this standard. Additional data that provides bases for this revision have also been published.<sup>2, 3</sup>

> This document was approved as an American National Standard in 1971. The present revision, which provides clarification of several items requested by users of the standard and more clearly identifies supporting documentation, was coordinated by N. Ketzlach of the U.S. Nuclear Regulatory Commission assisted by B. Ernst of American Nuclear Insurers, J. D. McCarthy of Rockwell International, Rocky Flats Plant, P. B. Adams of Corning Glass Company, and Martyn C. Evans of British Nuclear Fuels, plc.

> The development of the standard and its maintenance were performed under Subcommittee 8 of the Standards Committee of the American Nuclear Society. At the time of this approval of the revision, Subcommittee 8, Fissionable Materials Outside Reactors, had the following membership:

- J. T. Thomas, Chairman, Oak Ridge National Laboratory
- E. B. Johnson, Secretary, Oak Ridge National Laboratory
- F. M. Alcorn, Babcock and Wilcox Company
- H. K. Clark, Savannah River Laboratory
- E. D. Clayton, Battelle-Pacific Northwest Laboratories
- D. M. Dawson, Battelle Memorial Institute
- M. C. Evans, British Nuclear Fuels, plc
- N. Ketzlach, U.S. Nuclear Regulatory Commission
- R. Kiyose, University of Tokyo
- W. G. Morrison, Exxon Nuclear Company, Inc. (retired)
- D. R. Smith, Los Alamos National Laboratory
- G. E. Whitesides, Oak Ridge National Laboratory
- F. E. Woltz, Goodyear Atomic Corporation

<sup>&</sup>lt;sup>1</sup>J. P. Nichols, C. L. Schuske, and D. W. Magnuson, "Use of Borosilicate-Glass Raschig Rings as a Neutron Absorber in Solutions of Fissile Material," Y-CDC-8, Oak Ridge Y-12 Plant, Oak Ridge, Tennessee (1971). <sup>2</sup>P. B. Adams, Chapter 14 in *Ultrapurity*, M. Zief and R. Speights Editors, Marcel Dekker, Inc., New York (1972).

<sup>&</sup>lt;sup>3</sup>N. Ketzlach, Nucl. Tech., 42, 65 (1979).

The American National Standards Committee N16, Nuclear Criticality Safety, which reviewed and approved this standard in 1985, had the following membership:

#### D. Callihan, Chairman

#### E. B. Johnson, Secretary

Organization	Representative
American Institute of Chemical Engineers	A. F. Perge
American Nuclear Society	D. Callihan
American Society for Testing and Materials (Liaison only)	R. Artigas
Atomic Industrial Forum, Inc.	D. F. Cronin
E. I. du Pont de Nemours Company, Savannah River Site	W. R. Waltz
Exxon Nuclear Company	L. E. Hansen
Health Physics Society	F. W. Sanders
	I. C. Dyer (Alternate)
Institute of Nuclear Materials Management	C. L. Brown
	W. Mee (Alternate)
U.S. Department of Energy	L. Brinkerhoff
U.S. Nuclear Regulatory Commission	G. H. Bidinger
Individual Members	E. B. Johnson
Intibitati Members	H C Paxton

Contents	Se	ection	ıge
	1.	Scope	1
	2.	Definitions 2.1 Limitations 2.2 Shall, Should, and May 2.3 Glossary of Terms	1
	3.	General Specifications and Criteria  3.1 Chemical Environment  3.2 Physical Environment	1
	4.	Specifications for Rings 4.1 Composition 4.2 Chemical Acceptance Test 4.3 Ring Dimensions 4.4 Surface Finish 4.5 Mechanical Shock-Resistance Test	.2
	5.	Specifications for Packed Vessels  5.1 Unpacked Piping in Vessels  5.2 Determination of Level of the Rings  5.3 Allowable Volume of Solution in a Vessel Packed with Rings  5.4 Vessel Leakage  5.5 Determination of Glass Volume Fraction  5.6 Installation of Rings	.3
	6.	Maintenance Inspection 6.1 Settling 6.2 Solids Accumulation 6.3 Physical Properties 6.4 Boron Content of Rings 6.5 Inspection Intervals	.4 .5 .5
	7.	Maximum Specified Concentrations of Fissile Solutions	.6
	8.	References	.6
	Ap	pendix	.9
	Tal	ble 1 Maximum Permissible Concentrations of Homogeneous Solutions of Fissile Materials in Vessels of Unlimited Size Packed With Borosilicate-Glass Raschig Rings	.8
	Fig.	T. Tumbler Drum	0